


Selected Area 3



Lsec: 97.7 0 Cnts 0.000 keV Det: Octane Plus Det

eZAF Smart Quant Results with Carbon Coat 77nm

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	R	A	F
O K	8.65	21.83	5.06	19.73	0.04	1.23	0.89	0.49	1
Si K	17.01	24.44	16.31	8.89	0.10	1.12	0.95	0.64	1
Fe K	74.34	53.73	15.79	6.30	0.56	0.94	1.02	1	1